



ORGAICON™ Clear Conductive Screen-Printing Inks

Orgacon screen-printable inks are based on conductive polymer PEDOT/PSS and enable patterning of transparent conductive structures from plain down to resolution of 100 microns on flexible and rigid substrates such as PET, PC, PMMA, PI, and glass. Orgacon EL-P inks can achieve excellent characteristics such as flexibility and formability for electrodes of electroluminescent lamps, capacitive touch sensors, and membrane switches. Recommended screen is 350 polyester mesh for a wet film thickness of 1 mil. Resolutions of 100 microns can be achieved.

Manufactured by:



Grade	Typical applications	SER @ P120	SERxOD* ASTM D 1003	Viscosity (Pas), 25°C
EL-P3145	Patterned transparent conductive structures for EL and touch applications. Best for transparency.	350	8	> 14
EL-P3155	Patterned transparent conductive structures for LED- backlit capacitive sensors. Best for white light stability.	400	11	> 14
EL-P3165	Enhanced stability. Patterned transparent conductive structures for LED-backlit capacitive sensors for long-run printing	375	11	> 40
EL-P5015	Patterned transparent conductive fine structures for EL and touch applications, OPV ITO substitution. Highest conductivity. Preferred for achieving less than 20 micron dry film thickness.	190	18	> 50

* Lower value for SER x OD (Optical Density) indicates higher opto-electrical performance

Additional Information	
Solid Content	2.5 – 5.5% wt.
Color	dark blue
Shelf Life	12 months after fabrication date
Storage	Between 4°C and 25°C
Health & Safety	See Safety Data Sheet
Processing Recommendations	Contact us for processing guidelines

Authorized USA distributor:



Applied Ink Solutions®

MicroChem
200 Flanders Road
Westborough, MA 01581
Tel 617.965.5511