



SU-8 MicroSpray

Photoresist Aerosol Can

Description

Kayaku Advanced Material's aerosol spray can photoresists are well suited for a variety of micro-machining, and etching processes, requiring semi-conformal coatings on irregular or perforated substrates. SU-8 MicroSpray addresses many of the process and capital requirements for MEMS, microfluidics, opto-electronics and "one-up" printed circuit boards.


Applications

- Uniform coatings without spin coater tool
- Striation-free coatings over deep topography
- Perforated or irregular substrates
- Large substrates
- Microfluidic electrophoresis analysis
- Lab-on-Chip
- Patterned through-wafer vias
- "One up" PCBs
- Spray coater tool pre-evaluation
- Backside coatings
- Touch-up coatings

How to Use SU-8 MicroSpray

- Store can refrigerated for best use
- Place can at room temperature 1 hour prior to use
- Shake can vigorously 10 times
- Wait 5 minutes
- Make sure substrate is clean
- Use a spray distance of 3 inches from surface
- Spray surface with 6 passes and change direction of spray after 3 passes to form an overlapping pattern
- Wait 5 to 10 minutes (micro-bubbles will disappear)
- Bake coated substrate for 10 minutes at 95°C (200°F)
- Expose coated substrate to UV light (250 mJ/cm²)
- Bake again for 3 minutes at 95°C (200°F)
- Develop for 5 minutes in SU-8 Developer
- Rinse and dry

Coating Uniformity



9 µm +/- 3% (100 mm wafer)

| | |
|--------------------|---------|
| Mean | 9.14mm |
| Standard deviation | 0.24 mm |
| % Variability | 2.6% |



SU-8 MicroSpray Process Parameters

| | |
|--------------|--|
| Substrate: | Silicon |
| Photoresist: | SU-8 MicroSpray |
| Bake: | 10 minutes @ 95°C (200°F) |
| Coat: | Spray 6-9 right angle passes |
| Pause: | 20°C/5-10 minutes |
| Soft bake: | 10°C/95 minutes |
| Exposure: | EVG 620 350-450 nm, 400 mJ/cm ² |
| Develop: | SU-8 Developer 5 minutes |

Handling

Consult Safety Data Sheet (SDS) for details on the handling procedures and product hazards prior to use. If you have any questions regarding handling precautions or product hazards, please email productsafety@kayakuAM.com.

Storage

Store upright in original sealed containers in a dry area between 10°C and 21°C (50-70°F). Keep away from sources of ignition, light, heat, oxidants, acids and reducers. Do not use product after the expiration date (13 months from date of manufacture).

Disposal

The material and its container must be disposed in accordance with all local, state, federal and/or international regulations.

Disclaimer

Notwithstanding anything to the contrary contained in any sales documentation, e.g., purchase order forms, all sales are made on the following conditions:

All information contained in any Kayaku Advanced Materials product literature reflects our current knowledge on the subject and is, we believe, reliable. It is offered solely to provide possible suggestions for the customer's own experiments and is not a substitute for any testing by the customer to determine the suitability of any of Kayaku Advanced Materials products for any particular purpose. This information may be subject to revision as new

knowledge and experience becomes available, but Kayaku Advanced Materials assumes no obligation to update or revise any data previously furnished to a customer; and if currency of data becomes an issue, the customer should contact Kayaku Advanced Materials requesting updates. Since Kayaku Advanced Materials cannot anticipate all variations in actual end uses or in actual end-use conditions, it makes no claims, representations or warranties, express or implied including, without limitation any warranty of merchantability or fitness for a particular purpose; and the customer waives all of the same. Kayaku Advanced Materials expressly disclaims any responsibility or liability and assumes no responsibility or liability in connection with any use of this information including, without limitation, any use, handling, storage or possession of any Kayaku Advanced Materials products, or the application of any process described herein or the results desired or anything relating to the design of the customer's products. Nothing in this publication is to be considered as a license to operate under or a recommendation to infringe any patent right.